

JC CitraPass 3210

CITRIC ACID CLEANER

Medical & Pharma



- High performance citric acidic detergent to meet the high-quality demands of pharmaceutical and medical device industries
- Passivate 300 series, 17-4, and 400 series stainless steel alloys (ASTM 967, ASTM B600)
- Low foaming for high pressure applications
- Free rinsing and can be filtered to extend bath life
- Contains no added biocide (1 year shelf life)
- Complete lot traceability
- Biodegradable

NORMAL PROCESS

| | |
|-----------------------|------------------------------|
| Process: | Spray Wash Systems |
| Concentration: | 12-20% (normal range 12-15%) |
| Temperature: | 140°F-160°F/60°C-70°C |
| Rinse: | Yes |
| Dry: | Air |

PRODUCT PROPERTIES

| | |
|--------------------------|-------------------------------|
| Appearance: | Clear, straw colored liquid |
| PH Range: | 2-3 |
| Specific Gravity: | 1.16-1.17 g/mL at 25°C (77°F) |
| Water Soluble: | Soluble |

PRODUCT APPLICATION

spray wash

REMOVES THESE CONTAMINANTS

iron, light contaminants, fingerprints

SURFACE COMPATIBILITY

stainless steel, cobalt chrome, nickel alloys, and titanium

JC CitraPass 3210

CITRIC ACID CLEANER

Medical & Pharma

NORMAL CONTROL

Dropping Bottle Method (Jayco Chemical Solutions part number: Acidity Test Kit JYT002)

1. Take a sample of the JC CitraPass 3210 solution from the Bath with a beaker and allow to cool to room temperature.
2. Measure out 10 ml, using the graduated sample bottle provided in the titration kit.
3. Add 1-2 drops phenolphthalein indicator
4. Add dropwise 5.0N N sodium hydroxide (NaOH) while counting the drops and swirling the solution.
5. Stop adding the drops when color changes from colorless to pink.
6. Calculation :

$$\text{Concentration of JC CitraPass 3210 (\%)} = \text{Drops of 5.0N NaOH} \times 0.310$$

Conductivity

Below are readings taken with DI water. Jayco Chemical Solutions suggests making up known concentrations in customer's operating range and water for more accurate readings

| % | conductivity (mS/cm) |
|----|----------------------|
| 1 | 1.2 mS/cm |
| 2 | 1.7 mS/cm |
| 5 | 3.0 mS/cm |
| 10 | 4.0 mS/cm |
| 15 | 4.9 mS/cm |

HANDLING AND SAFETY CONSIDERATIONS

Consult product safety data sheet for handling considerations, hazard information, and first aid procedures.

OTHER INFORMATION

No warranty, expressed or implied of merchantability fitness for a particular purpose or otherwise, is made. Buyer assumes all risk of use, storage and handling. JAYCO Chemical Solutions shall not be made liable for any incidental or consequential damages arising directly or indirectly in connection with the purchase, storage, handling or disposal of this product.